

# Technical Information

## K H I - High Impact CPP Films

Standard Thickness 25, 30, 35, 40, 50 microns

- Description : A Coextruded Cast Polypropylene Film with two side heat sealable layer.  
The specialty of this film is its excellence impact strength at low temperature.
- Treatment : One side corona treated.
- Features : - Excellent heat seal strength.  
- High clarity and gloss  
- Excellent impact strength at low temperature.  
- Low static property.

PROPERTIES	TESTINGS METHOD	TYPICAL VALUE (25)*	UNIT
------------	-----------------	---------------------	------

### MECHANICAL

Tensile Strength	MD	ASTM D - 882	> 4.0	Kg / mm <sup>2</sup>
	TD		> 2.0	
Elongation	MD	ASTM D - 882	> 800	%
	TD		> 800	

### PHYSICAL

Coefficient of Friction	Film to Film (Ntr/ntr)	ASTM D - 1894	0.4 Max	-
Haze		ASTM D - 1003	3.5 Max	%
Heat Seal Range		-	115 - 125	°C
Heat Seal Strength		BTI Methode 125°C / 1bar / 1 sec	> 400	g / 15mm

### THERMAL

Thermal Shrinkage (AT 120 °C / 15Min)	MD	ASTM D - 1204	1.0 Max	%
	TD		1.0 Max	

### BARRIER

WVTR		ASTM F- 1249	< 10	g / m <sup>2</sup> / day 38°C / 90% RH
O <sub>2</sub> TR		ASTM F - 1927	< 3000	cc / m <sup>2</sup> / day 23°C
Corona (Surface Tension)		ASTM D - 2578	≥ 38	Dyne / Cm

\*) The Above data are given for reference only

### GENERAL INFORMATION

- Slit Width mm. - As per customer requirement
- Standard Length meter - 4.000 / 6.000 / 8.000

## PT. BHINEKA TATAMULYA INDUSTRI

### OFFICE :

Jl. Mampang Prapatan Raya No. 2 D-E  
Jakarta 12790 - INDONESIA  
Telp. : 62-21 791 84081  
Fax. : 62-21 791 84178  
E-mail : bhineka@cbn.net.id  
Website : www.ptbhineka.com

### FACTORY :

Jl. Raya DKI (Pangkalan V) KM. 2  
Bantar Gebang, Bekasi 17310  
INDONESIA  
Telp. : 62-21 825 0191 - 92  
Fax. : 62-21 825 0190