

Technical Information

K K K - Very Thick Sealing layer CPP Films

Standard Thickness 25, 30, 35, 40 microns

- Description : A Coextruded Cast Polypropylene Film with specialty very thick sealing layer.
 Application : **KKK** is usually applied for lamination with BOPP, NYLON and other substrates.
 It is applicable for either extrusion or dry lamination.
 Treatment : One side corona treated.
 Features : - Good moisture barrier.
 - Excellent heat seal strength
 - High clarity and gloss

PROPERTIES	TESTINGS METHOD	TYPICAL VALUE (25)*	UNIT
------------	-----------------	---------------------	------

MECHANICAL

Tensile Strength	MD	ASTM D - 882	> 4.0	Kg / mm ²
	TD		> 2.0	
Elongation	MD	ASTM D - 882	> 500	%
	TD		> 500	

PHYSICAL

Coefficient of Friction	Film to Film (Ntr/ntr)	ASTM D - 1894	0.4 Max	-
Haze		ASTM D 1003	5.0 Max	%
Heat Seal Range		-	115 - 125	°C
Heat Seal Strength		BTI Methode 125°C / 1bar / 1 sec	> 400	g / 15mm

THERMAL

Thermal Shrinkage (AT 120 °C / 15Min)	MD	ASTM D - 1204	1.0 Max	%
	TD		1.0 Max	

BARRIER

WVTR		ASTM F- 1249	< 10	g / m ² / day 38°C / 90% RH
O ₂ TR		ASTM F - 1927	< 3000	cc / m ² / day 23°C
Corona (Surface Tension)		ASTM D - 2578	≥ 38	Dyne / Cm

*) The Above data are given for reference only

GENERAL INFORMATION

- Slit Width mm. - as per customer requirement
- Standard Length meter - 4.000 / 6.000 / 8.000

PT. BHINEKA TATAMULYA INDUSTRI

OFFICE :

Jl. Mampang Prapatan Raya No. 2 D-E
 Jakarta 12790 - INDONESIA
 Telp. : 62-21 7918 4081
 Fax. : 62-21 7918 4178
 E-mail : bhineka@cbn.net.id

FACTORY :

Jl. Raya DKI (Pangkalan V) KM. 2
 Bantar Gebang, Bekasi 17310
 INDONESIA
 Telp. : 62-21 825 0191 - 92
 Fax. : 62-21 825 0190