

# Technical Information

## KVR 60 - High Retort CPP Films

Standard Thickness 40, 50, 60, 70, 80 microns

Description : A Coextruded Cast Polypropylene Film for high retort packaging and good impact properties in freezing condition.  
 Application : **KVR** is usually applied for dry-lamination with NYLON or PET  
 Treatment : One side corona treated.  
 Features : - Heat resistance at 140°C  
 - Good moisture barrier.

PROPERTIES	TESTINGS METHOD	TYPICAL VALUE (60)*	UNIT
------------	-----------------	---------------------	------

### MECHANICAL

Tensile Strength	MD	ASTM D - 882	> 4.0	Kg / mm <sup>2</sup>
	TD		> 2.0	
Elongation	MD	ASTM D - 882	> 500	%
	TD		> 500	

### PHYSICAL

Coefficient of Friction	Film to Film (Ntr/ntr)	ASTM D - 1894	0.9 Max	-
Haze		ASTM D - 1003	60 Max	%
Heat Seal Range		-	> 150	°C
Heat Seal Strength		BTI Methode 165°C / 1bar / 1 sec	> 800	g / 15mm

### THERMAL

Thermal Shrinkage (AT 120 °C / 15Min)	MD	ASTM D - 1204	1.0 Max	%
	TD		1.0 Max	

### BARRIER

WVTR		ASTM F- 1249	< 6	g / m <sup>2</sup> / day 38°C / 90% RH
O <sub>2</sub> TR		ASTM F - 1927	< 1500	cc / m <sup>2</sup> / day 23°C
Corona (Surface Tension)		ASTM D - 2578	≥ 38	Dyne / Cm

\*) The Above data are given for reference only

### GENERAL INFORMATION

- Slit Width mm. - As per customer requirement
- Standard Length meter - 2.000 / 3.000 / 4.000

### PT. BHINEKA TATAMULYA INDUSTRI

#### OFFICE :

Jl. Mampang Prapatan Raya No. 2 D-E  
 Jakarta 12790 - INDONESIA  
 Telp. : 62-21 791 84081  
 Fax. : 62-21 791 84178  
 E-mail : bhineka@cbn.net.id  
 Website : www.ptbhineka.com

#### FACTORY :

Jl. Raya DKI (Pangkalan V) KM. 2  
 Bantar Gebang, Bekasi 17310  
 INDONESIA  
 Telp. : 62-21 825 0191 - 92  
 Fax. : 62-21 825 0190